



Always the right solution

- recommended
- suited
- not recommended

	100% Cotton	100% Polyester	Sublimated Polyester	Cotton Polyester Blends	100% Nylon	Nylon Blends	Easy Weeding	Iron	Machine Wash	Sublimation	Stretchable	Thin	Sticky Carrier	Multi-Layer Application	Peel	Application
CAD-CUT® Premium Plus	●	●	–	●	–	–	easy weed	iron	60°		stretch	down	up			150°C 5 sec
CAD-CUT® Premium Plus Sublistop	○	●	●	○	–	–	easy weed	iron	60°	sublistop S T S T S			up	up		130°C 10sec
CAD-CUT® SportsFilm	●	●	–	●	–	–	easy weed	iron	60°			down	up	up	HOT PEEL	130°C 10sec
CAD-CUT® Flock	●	●	–	●	○	○		iron	60°				up			165°C 15 se
CAD-CUT® Effect	●	●	●	●	–	–		iron	40°				up			150°C 10 sec
CAD-CUT® Glitter	●	●	●	●	–	–		iron	40°				up			150°C 10 sec
CAD-CUT® Silicon 100, 200 & 500	●	●	○	●	–	–	easy weed	iron	60°							150°C 10 sec
CAD-CUT® Reflective	●	●	●	●	–	●	easy weed	iron	30°			down				
CAD-CUT® Glow	●	●	–	●	–	–	easy weed	iron	30°			down				150°C 10 sec
CAD-CUT® Soft Metallic	●	●	–	●	●	●	easy weed	iron	40°		stretch	down	up	up		150°C 10 sec
CAD-COLOR® SuperTEK™ Opaque	●	●	○	●	●	●		iron	60°		stretch	MEDIUM				150°C 5 sec
CAD-COLOR® SportsFilm	●	●	○	●	–	–		iron	60°			MEDIUM			HOT PEEL	160°C 5 sec
CAD-COLOR® SuperTEK™ Sublistop	●	●	●	●	○	○		iron	40°	sublistop S T S T S	stretch	MEDIUM				150°C 5 sec
CAD-COLOR® Clear	●	●	○	●	●	●		iron	40°		stretch	MEDIUM				150°C 5 sec
CAD-COLOR® Glow in the Dark	●	●	○	●	–	–		iron	40°			MEDIUM				150°C 12sec
CAD-COLOR® Flexi Film	●	●	●	●	–	–		iron	30°			MEDIUM			HOT PEEL	130°C 10sec
CAD-COLOR® Glitter	●	●	–	●	●	●		iron	30°			MEDIUM			HOT PEEL	150°C 12sec