### BF PRINTOO-BF PRINTO1

**PRINT&CUT** 



### PRODUCT DESCRIPTION

BF PRINT00 (semi-matte) and BF PRINT01 (matte) are two polyurethane white films printable with solvent, eco-solvent and latex inks and are suitable for heat transfer on cotton fabrics, polyester and acrylic garments.

Very small letters and logos can be easily cut by all current cutting plotters after the printing process thanks to the self-adhesive PET film carrier.

We recommend using BF MYLAR as a transfer tape.

### **TECHNICAL DATA**



Film: PU/Polyurethane



Thickness: 90µ (±5%)



Liner: adhesive PET



Finish: BF PRINT00 semi-matte BF PRINT01 matte



Inks: solvent, eco-solvent, latex

## APPLICATION STEPS

- Print do not mirror
- Cut 45° blade
- Weed excess material
- Apply BF MYLAR remove air bubbles
- Remove from liner
- Turn on your heat press heat to 140°C/285°F
- Place your graphic on the garment
- Press it 140°C/285°F for 10 seconds
- Remove BF MYLAR hot

# **PLOTTER SETTING**

Cut settings: do not mirror



Minimum cut: 0,5 cm

### **APPLICATION**



Temperature: 140°C - 285°F



Time: 10"

Blade: 45°



Liner removal: hot



Pressure: medium - 3,5 bar - 50 PSI



Textile: organic, polyester, mixed

### **SIZES**

H 50 cm	L	25 mt / 12,5 mt / 5 mt
H 75 cm	L	25 mt (upon request)
H 100 cm	L	25 mt (upon request)
H 150 cm	L	25 mt (upon request)

Oeko-Tex Standard 100 Class I



Comply with regulation REACH n°1907/2006/EU

### WASH RESISTANCE

First wash after application	wait 12 hours
Max wash temperature*	90°C / 195°F
Dry clean	×
Dryer	×

stTemperatures related on heat transfer vinyl; for the inks features, refer to the data sheet inks producer's.

#### SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information above mentioned in this page. Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications. Rev\_2021/03

follow us









